

## AQUA MS LASUR

Water-based wax-effect impregnating finishing treatment

3046-a January 2016

### Description

**Product:** AQUA MS LASUR is a water-based wax-effect impregnating finishing treatment, for protecting and enhancing wood. It is free from biocides.

**Applications:** for all types of wood both indoor and outdoor and particularly recommended for wood with partial and total dimensional stability such as windows and external doors. It should not be used indoors in extremely humid environments such as covered swimming pools, saunas, etc.

**Protection:** AQUA MS LASUR protects wood from humidity and UV radiation.

**Colours:** 00 – colourless, 01 – oak, 03 – chestnut, 04 – walnut, 10 – light walnut, 27 – teak, 35 – wenge, 91 – covering white

**Packaging:** 0.75 – 2.5 litres in tins.

### Technical data

**Specific weight:** approx. 1.03 – 1.05 kg/l at +20 °C

**Flash point:** not applicable.

**Viscosity:** 150-200 s/ DIN cup 2 mm at +20 °C

**Drying time** after 2-4 hours according to the type of wood, the quantity of paint applied and the atmospheric conditions. In low temperatures and/or high humidity the drying time is prolonged proportionally.

**Odour:** very weak odour; odourless once dry.

**Storage:** 3 years in the original closed containers. Store at a cool temperature protected from frost. Close partially used tins carefully; if there is a particularly large air space transfer to smaller containers.

### How to apply

**General:** mix the product well before using. Do not work at temperatures below +10°C (environment, surface or product).

**Application systems:** brush, spray

**Surface preparation:** the wood to be treated must be dry and free from dust and grease. Do not apply to wood with a moisture content over 15%. Remove any poorly anchored old paint or varnish. Clean any resinous areas or pockets on the surface with nitro thinner.

**Application advice:** outdoor wood should be pre-treated with a suitable protective primer, chosen on the basis of the degree of risk, to protect it from attack by animal and/or vegetable parasites, for example Hydrogrund.

Wood located in indoor environments does not normally need treating with a protective primer, other than in particular situations such as when insect attack has been detected or for construction elements in damp environments or when exposed to water sprays, e.g. in showers, or when applied to starch-rich wood, typically from broad-leaf trees, for example abachi, limba, ramin, oak sapwood.

If a solvent-based protective primer has been chosen, before applying the following coat, check that the solvent has completely evaporated and that the binder is perfectly dry.

If large surfaces or highly absorbent types of wood are to be treated using a brush, moisten the wood with a damp sponge before application. To avoid leaving re-start marks, apply the product in the direction of the grain.

End-grain wood should be treated with more coats of AQUA MS LASUR to reduce water-absorption as much as possible.

Metal fixings (nails, screws, hinges etc.) used on the surface to be treated and other metal parts that may come into contact with the product must be in a corrosion-resistant material.

### Recommended treatments:

- New outdoor wood:	1-2 x Hydrogrund Plus 1-2 x Wasserlasur 1-2 x AQUA MS LASUR, with intermediate sanding down (280 grain).
- New indoor wood:	1-2 x AQUA MS LASUR, according to the degree of finishing required (if using 2 coats, sand down between them, 280 grain).

## AQUA MS LASUR

Water-based wax-effect impregnating finishing treatment

3046-a January 2016

- Restoration of outdoor wood:	Remove any existing paint or varnish that is not well bonded to the surface; clean and sand down the surface to improve adhesion. Then 1-2 x AQUA MS LASUR, with intermediate sanding down (280 grain). If the wood has been restored as new, follow the instructions for new wood.
- Restoration of indoor wood:	Remove any existing paint or varnish that is not well bonded to the surface; clean and sand down the surface to improve adhesion. Then 1-2 x AQUA MS LASUR, according to the state of the surface and to the degree of finishing required (if using 2 coats, sand down between them, 280 grain). If the wood has been restored as new, follow the instructions for new wood.

Colourless AQUA LIGNEX I does not contain any pigments and therefore does not provide UV radiation protection. It is therefore advisable to use this outdoors only as a top coat on coloured paint or to lighten dark shades. The effect of individual colours will vary with the type of wood and therefore it is always advisable to do a test application. We recommend checking the state of outdoor paint 2 years from application, particularly for items with south-west exposure.

**Consumption:** approx. 10 - 12 m<sup>2</sup>/l per coat.

**Dilution:** AQUA MS LASUR is ready to use with a brush. If necessary, dilute with water.

**Over-painting:** in normal conditions it can be sanded down and over-painted after 4 hours.

**Tool cleaning:** with water immediately after use.

### Special instructions

Even when using products low in hazardous substances, the usual precautions should be taken for working with paint. Always ensure adequate ventilation. Keep out of the reach of children. In the event of contact with the skin or eyes, rinse immediately and carefully with water. Cover electrical switches and cables properly to avoid short circuits. Do not let the product pollute water courses and drainage water that may penetrate the soil.

**Disposal:** dispose of the product and its residues according to current regulations.

**Water hazard class:** WGK 1 low hazard (self-classification).

**VbF classification:** not classified.

**ADR/RID:** not applicable.

*The above instructions are consistent with the most recent information on the development and use of our product. Because we have no control over the onsite use and application of the product, we may only be held liable for the quality of the product as supplied. If in doubt please contact our technical consultancy service.*