

STUFEX[®] R 1551
Single-component water-based primer

Rev. January 2014

Applications

Single-component, water-based primer for parquet and other floorings and coverings in general. It closes the pores to water and is particularly recommended as a base coat for subsequent topcoats of Stufex R 1600 / R 2660 water-based varnish (glossy/opaque). Ultra quick-drying and does not alter the properties of the wood. Designed for painting cycles to be carried out quickly, it can be sanded down after about 1 hour.

Technical data

PRODUCT IDENTIFICATION DATA	
Appearance	Whitish liquid
Test viscosity (DIN 3)	40 +/- 3 sec.
Conservation	In the original container kept tightly shut, avoiding low temperatures. Use preferably within 6 months. PROTECT FROM FROST.
APPLICATION DATA	
Application temperature	Do not apply in temperatures below +10°C
Drying time	
Dry to the touch	30 minutes
Completely dry	1 hour
Sanding down	1-1,5 hours
Dilution	In high temperatures add a maximum quantity of 2% STUFEX 019 retardant thinner
How to apply	Paintbrush Roller Spray

The above information has been obtained from an application of 150 microns moist, at a temperature of 20°C and relative humidity of 60%. A different thickness and/or temperature and/or relative humidity may lead to a variation in these data.

How to apply

PREPARATION

Ensure that the wooden surfaces to be treated are free from dust and greasy substances (wax, silicone, oil, etc.) that could compromise the product's adhesion. Filter the product to eliminate any polymerised residues formed on the sides or stopper of the packaging. We recommend mixing thoroughly before use and do not exceed the quantities indicated.

STUFEX[®] R 1551
Single-component water-based primer

Rev. January 2014

APPLICATION

Proceed as follows for an excellent result.

1. One coat of Stufex R 1551 primer and one or two coats of Stufex R 1600 or R 2660 varnish according to the desired degree of finish.
2. The surface of the Stufex R 1551 base must be sanded down between the following coats using fine-grain sandpaper (220 - 240), which can be done after ca. 1 hour (in optimal environmental conditions).

If varnishing difficult wood (olive, exotic wood such as iroko, teak, etc.) we recommend using a more traditional solvent-based impregnating primer such as Stufex R 31.

(Tools can be cleaned with water)

Yield

The ideal quantity to apply is

80-100 g/m²

Packaging

The product is supplied in tins of

20kg - 10kg - 5kg

The instructions provided in this document are consistent with the most recently available information on the development and use of our product. Because we have no control over the onsite use and application of the product, we may only be held liable for the quality of the product as supplied.