

STUFEX[®] PR 99

Single-component water-based consolidator

Rev. January 2014

Applications

Sealing water-based consolidator for concrete under-surfaces that are dusty or poorly consolidated upon which parquet is to be laid using a water-based adhesive.

Technical data

PRODUCT IDENTIFICATION DATA

Colour	Transparent
Specific weight	1.01+/- 0.05 gr/cm ³
Test viscosity (DIN 2)	52 +/- 3 sec.
Conservation	In the original container kept tightly shut, avoiding low temperatures. Use preferably within 6 months. PROTECT FROM FROST.

APPLICATION DATA

Dilution	Ready to use
Drying time	1 hour at 23°C
How to apply	Paintbrush Roller

The above information applies to a temperature of 20°C and relative humidity of 60%. A different temperature and/or relative humidity can lead to variations in these data.

How to apply

PREPARATION

To obtain perfect anchorage of water-based vinyl adhesive, the surface must be suitable, non-friable, free from dust and standard moisture-content.

Thoroughly clean the surface to be treated, removing all traces of oil, grease, wax and varnish stains. Shake well before using.

APPLICATION

A single coat of Stufex PR 99 may be sufficient. If the surface is very friable a second coat can be applied.

The parquet can be laid 8-10 hours after the last coat of Stufex PR 99 using water-based adhesive only.

Consumption

The ideal quantity to apply is

120-220 g/m²

Packaging

The product is supplied in tins of

5kg

The instructions provided in this document are consistent with the most recently available information on the development and use of our product. Because we have no control over the onsite use and application of the product, we may only be held liable for the quality of the product as supplied.